

Corten Steel A Plate

EQUIVALENT GRADE

		Steel	Grade		Material No.				
High Tensile Steel	TKS Standard	EN Standard	ASTM Standard	ASTM Standard	iviaterial NO.				
Plate	CORTEN A	S355JOW	ASTM 588 GRADE A	ASTM A 242 TYPE 2	1.8946				

SPECIFICATION

Thickness	0.8 mm to 50mm
Width	750mm to 1500mm
Length	upto 12,000mm

CHEMICAL COMPOSITION

(CHEMICAL COMPOS	SITION		b. -	00110	100				
	Grade	%C	%Si	%Mn	%P	%S	%Cr	%Cu	% V	%Ni
	CORTEN A	0.12	0.25-0.75	0.20-0.50	0.07-0.15	0.030	0.50-1.25	0.25-0.55		0.65

MECHANICAL PROPERTIES

Grade	Minimum yield point ReH Mpa *)	Tensile strength Rm MPa	Minimum elongation A (Lo=5.65 √So) %
CORTEN A	355	470-630	20

Plate Size available Ex-Stock

1mm	2mm	3mm	4mı	m 6mr	n 8mm	10mm	12mm	14mm	16mm	20mm	25mm	30mm	32mm	36m	m 40r	nm
45mm	50mn	63m	nm	70mm	72mm	75mm	80mm	90mm	100mm	110mm	130mm	150mr	m 170r	nm	180mm	200mm
230mm	270r	nm 3	00mn	n												

Makes/Brands Available: SAIL, TATA, JSW, JSPL, Essar, POSCO, Uttam

DISCLAIMER: while great care has been taken to ensure the accuracy of all information contained in this document, Jaguar Steel India hereby disclaims any and all responsibility or liability that may be asserted or claimed arising from, or claimed to have arisen from, reliance upon the use or the interpretation of this document by any person This document may be subject to change at any time without

> CONTACT INFO: Address: B-8, 1st Floor, Nehru Ground, Faridabad, Haryana, 121001, Email: sales@jaguarsteel.com, Phone: +91-8447070292, +91-9899747099, https://www.jaguarsteel.com/